

# STOBIGYM EN 6.2.2

Punctual Deformation Indoor System



**Support** Non porous concrete/asphalt

	Product	Quantity kg/m <sup>2</sup>
<b>Glue</b>	<b>Stobielast® S 113.03</b> (2-components)	1.00 kg
<b>Base mat</b> 6 mm	<b>Prefabricated foam rubber mat</b> (Ref : Sportec premium)	
<b>Pore sealer</b>	<b>Stobielast® S 129.36</b> (2-components)	0.25 kg
<b>Self levelling</b> 2.0 mm	<b>Stobielast® S 148.[..]</b> (2-components)	2.80 kg
<b>Top coat</b>	<b>Stobielast® S 165.[..]</b> (2- components)	0.16 kg
<b>Line marking</b>	<b>Stobielast® S 166.[..]</b> (2- components)	ml/kg acc. game
	[..] = the last two digits of our product codes mark the individual colour of our system.	
<b>Total thickness</b>	8 mm	

**Application** Multisport qualification Sport-halls

**Agreement** European Standard: EN14904\*  
Euroclasses : EN 13501-1\*\*

[\*] : Sport halls European specifications - Indoor surfaces for multi-sports use

[\*\*] : European classification of fire performance characteristics for building products

Standard EN14904	P1 Class
Euroclasses EN13501-1	Cfl S1

**Issue** November 2014

**Stockmeier Uréthanes France SAS**  
8, Rue de l'Industrie  
Z.I. Est  
68700 Cernay  
FRANCE  
T +33 (0)3 89 75 70 70  
F +33 (0)3 89 75 70 81  
snad@snad.fr  
urethanes.fr@stockmeier.com  
www.stockmeier-urethanes.com